

PRO STAR RUBBER CO., LTD.

24/2 Soi Sukhumvit 35, Sukhumvit Road, Kwaeng Klongton Nua, Khet Wattana, Bangkok 10110 Thailand Tel: (+66) 2-259-9284 Fax: (+66) 2-662-0559

Specification Rubber Test Results

This is to certify that, at the request of customer, we have performed the quality inspection of the under mentioned goods:

Commodity

SKIM BLOCK

Laboratory

RUBBER ESTATE ORGANIZATION

Date Tested

20/08/13

Test Result

Date tested: 20/08/2013

| Your ref. | Dirt | Ash | VM | N | WALLANCE | | | Mooney |
|-----------|-------|------|------|------|----------|------|------|-----------------------------|
| | % | % | % | % | Ро | P30 | PRI | Viscosity ML 1+4 (100°C) |
| STR20 | 0.188 | 1.06 | 0.20 | 2.73 | 62.0 | 8.0 | 12.9 | 99.2 |
| | | | | | | | | |
| AVG | 0.188 | 1.06 | 0.20 | 2.73 | 62.0 | 33.0 | 12.9 | 99.2 |

We certify that all the tests which we have carried out on the samples submitted to us are consistent with the description.



Date of issue: 25 / /0/20/3

For and on behalf of PRO STAR RUBBER CO., LTD